

## REDBAC Acid Resistant Grout – K-011

<b>Description:</b>	REDBAC Acid-Resistant Grout is a three component, 100 % solids epoxy resin system combining high mechanical strength with resistance to sulfuric acid, most fuels, oils, and water. REDBAC Acid-Resistant Grout mixes easily, self-levels, and cures quickly to minimize downtime and production loss. K-011 is an ideal grout for mining, oil field, and chemical plant applications.			
<b>Intended Use:</b>	<ul style="list-style-type: none"> <li>• Grouting machine bases</li> <li>• Setting sole plates</li> <li>• Setting anchor bolts</li> <li>• Repairing deteriorated foundations</li> <li>• Setting leveling wedges</li> <li>• Enhancing concrete surfaces</li> </ul>			
<b>Application Guidelines:</b>	<p>The working time (the time you have before the grout sets) will vary according to the air temperature. The average working time at 70 °F (21 °C) will be about 20 minutes. In cooler weather you will have more time to pour, in hotter weather you will have less time.</p> <p>The average cure time from the last pour to machinery start-up will be 24 hours at 70 °F (21 °C). In cool weather, the grout will cure and develop strength more slowly than in hot weather</p>			
<b>Handling Properties:</b>	SPECIFIC GRAVITY, g/cm <sup>3</sup>	2.07		ASTM D 792
	MIXED VISCOSITY, cP or mPa.s	20,000		ASTM D 2196
	WORKING TIME, min	20		
	GEL TIME , min	50-60		ASTM D 2471
	MAXIMUM DEPTH OF POUR, in. (cm)	2	(5.1)	
<b>Physical Properties:</b>	COMPRESSIVE STRENGTH , psi (MPa)			ASTM D 695
	after 6 h	11,200	(77)	
	3 days	16,700	(115)	
	7 days	17,500	(120)	
	TENSILE STRENGTH, psi (MPa)	3,000	(21)	ASTM D 638
	FLEXURAL STRENGTH, psi (MPa)	6,000	(41)	ASTM D 790
	HEAT DISTORTION TEMPERATURE, °F (°C)	227	(108)	ASTM D 648
	MAXIMUM CONTINUOUS SERVICE TEMPERATURE, °F (°C)	325	(163)	
	(for non load-bearing applications)			
	HARDNESS, Shore D	90		ASTM D 2240
	WATER ABSORPTION (30 days @ 72 °F or 22 °C), %	0.24		ASTM D 2583
	CREEP (24 hours @ 600 psi or 4 MPa load @ 150 °F (66 °C), in./in. or cm/cm	5.59 x 10 <sup>-3</sup>		ASTM C 181
<b>Chemical Resistance:</b>	REDBAC Acid-Resistant Grout is resistant to these chemicals:			
	70 % Sulfuric Acid	50 % Phosphoric Acid	Motor Oil	Mineral Spirits
	10 % Hydrochloric Acid	Ammonium Hydroxide	Leaded Gas	Trichloroethane
	10 % Nitric Acid	50 % Sodium Hydroxide	Unleaded Gas	15% Sodium Hypochlorite
	Xylene	Methanol	Acetone	
	Diesel Fuel	Kerosene	Water	

**Surface Preparation:**

**CONCRETE PREPARATION:** Remove all oil, grease, or contaminated concrete. Chip the surface down to sound aggregate. The concrete must be **dry** and have no water in the anchor bolt holes. Light sand blasting or acid etching surface preparation procedures may result in poor bond and should be avoided. Do not prime or seal concrete surfaces.

**FORMING:** Standard wood or metal forming may be used. The forms should be protected with heavy coats of paste wax, grease, or form release agent. Wrapping the forms with heavy plastic is acceptable. The forms must be caulked and sealed to a liquid-tight condition.

When placing forms for grouting, it is absolutely necessary that the top of the forms be at least half way up the sides of the base plate or machine base. Placing the grout just to the bottom of the base plate will result in an improper grout job. If the forms cannot be placed half way up the side of the machine base, the minimum distance is 3/4 inch (1.9 cm) above the bottom of the machine base.

The forms should be placed between 2 and 6 inches (between 5 and 15 cm) away from the perimeter of the machine base to allow for the air to escape and to provide for a grout shoulder around the base plate.

**PREPARATION OF METAL SURFACES:** Base plates or sole plates to be grouted should be sand blasted to a "white metal" condition. If it is impossible to grout within 24 hours of sand blasting, the surfaces should be primed with a high-quality primer. Do not use porch and deck enamel or red-lead primer.

**Mixing:**

Mix the Resin (Part A) and the Hardener (Part B) for 2-3 minutes with a slow speed (500 rpm or less) drill and Jiffy Mixer (mixing paddle). Add aggregate (Part C), mix to a uniform consistency. Pour the material into the form.

**Application:**

Always sweep (pour) from one side of the base toward the other to eliminate entrapped air. The storage temperature of the unmixed kits of REDBAC will greatly affect both the ease of pouring and the cure time. For best results, REDBAC kits should be stored in a warm room for at least 24 hours before use. Do not pour if the grout is below 50 °F (10 °C).

During cold weather (below 50 °F or 10 °C), it is important that the foundation be enclosed and maintained above 50 °F (10 °C). The cure time of the grout will be longer during cold weather and it is important that the grouted area be kept warm (above 50 °F or 10 °C) until the grout has cured completely.

Uncured REDBAC grout can be removed from tools and equipment with Copps Enviro Kleen or isopropyl alcohol.

**Packaging:**

K-011-63: 5 Gallon = 860 in.<sup>3</sup> = 0.5 ft.<sup>3</sup> = 8.93 l  
K-011-125: Bulk = 1700 in.<sup>3</sup> = 1.0 ft.<sup>3</sup> = 0.03 m<sup>3</sup>

**SAFETY PRECAUTIONS**

Avoid breathing of vapors. Forced local exhaust is recommended to effectively minimize exposure. NIOSH approved, organic vapor respirators and forced exhaust are recommended in confined areas, or when conditions (such as heated polymers, sanding) may cause high vapor concentrations.

**DO NOT WELD ON, BURN OR TORCH ON OR NEAR, ANY EPOXY MATERIAL. HAZARDOUS VAPOR IS RELEASED WHEN AN EPOXY IS BURNED.**

Avoid skin or eye contact. Wash skin with soap and water if contact occurs. If eye contact occurs flush with water for 15 minutes and obtain medical attention. Read and understand all cautions on can labels and safety data sheets before using this material.

**FOR INDUSTRIAL USE ONLY****WARRANTY AND DISCLAIMER**

Copps Industries, Inc. gives no warranty, express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product. Copps Industries, Inc. shall be in no way responsible for the proper use and service of the product. The information given in this publication is considered to be accurate and reliable and is provided as a service only. Physical properties shown are typical. Actual properties are dependent on curing conditions and degree of cure. Any information or suggestions given are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.

TB#4011 (05/09/17)