

## ARMORGARD STEEL COAT

<b>Description:</b>	Armorgard Steel Coat is a 100 % solids, self-leveling, room temperature cure form coating. It was formulated to provide a hard, tough coating for metal concrete forms used for precast, tilt-up, slip form or cast-in-place applications. Armorgard Steel Coat does not contain VOC's or butyl glycidyl ether (BGE)*.		
<b>Product Advantages:</b>	<ul style="list-style-type: none"> <li>● EXTREMELY DURABLE SURFACE</li> <li>● USER-FRIENDLY MIX RATIO</li> <li>● STRONG ADHESION TO PREPARED STEEL</li> <li>● SINGLE COAT APPLICATION</li> </ul>		
<b>Application Guidelines:</b>	Normal application thickness is 25-35 mil (0.64-0.89 mm). Application may vary depending on the porosity and roughness of the surface.		
<b>Handling Properties:</b>	MIX RATIO, pbv (pbw)	1/1	(1.2/1)
	COLOR	Light Amber	
	MIXED VISCOSITY, cP or mPa.s	8,600	ASTM D 2196
	WORKING TIME, min	25	
	GEL TIME, min	33	ASTM D 2471
	TACK-FREE TIME, h	5-6	
	INITIAL CURE, h	9-12	
	APPLICATION TEMPERATURE, °F (°C)		
	Ideal	70-80	(21-27)
	COVERAGE* @ 25 mil (0.64 mm), ft <sup>2</sup> /gal	63	
	*Varies with porosity of surface		
<b>Physical Properties:</b>	HARDNESS, Shore D	83	ASTM D 2240
	MAXIMUM SERVICE TEMPERATURE, °F (°C)	135	(57)
	Armorgard Steel Coat will soften when exposed to extreme precast temperatures. A temperature of no greater than 135 °F (57 °C) is recommended when removing forms coated with Armorgard Steel Coat.		

\*Butyl Glycidyl Ether. The EPA (SARA Title III, section 312) lists it (BGE) as "Toxic" (per ANSI Z129.1) by skin absorption and an immediate health hazard.

<b>Surface Preparation:</b>	To achieve excellent adhesion, the substrate must be clean and free of all loose and foreign material. Oils, grease, waxes or other contaminants <u>must</u> be removed prior to coating. The surface should be prepared to a near white metal finish per standard NACE 2/SSPC-SP 10. Armorgard Steel Coat will not bond to a contaminated surface.
<b>Mixing:</b>	The storage temperature of Armorgard Steel Coat will greatly affect the ease of mixing, application and curing time. For best results, Armorgard Steel Coat should be stored at <b>(60-80 °F or 16-27 °C)</b> for at least 24 hours before use. Mix 1 part A (resin) to 1 part B (hardener) for 3 minutes using a Jiffy Mixer and a slow speed drill. Mix at slow speed (less than 500 rpm) to avoid air entrainment. When adding part B to part A, be sure to scrape the sides of the hardener (part B) container in order to remove all of the hardener. This is essential to maintain proper mix ratio. DO NOT mix more material than can be used within the stated working time. REMEMBER - you will have less working time at higher temperatures.
<b>Application:</b>	Armorgard Steel Coat can be applied with a grooved fiberglass or aluminum roller.

### **SAFETY PRECAUTIONS**

Mix and pour in a well-ventilated area. Avoid contact with skin and eyes. If contact does occur, wash skin with soap and water and seek medical help. Read and understand all CAUTIONS on container labels and safety data sheets before using this material.

Avoid breathing of vapors. Forced local exhaust is recommended to effectively minimize exposure. NIOSH approved, organic vapor respirators and forced exhaust are recommended in confined areas, or when conditions (such as heated polymers, sanding) may cause high vapor concentrations. **DO NOT WELD ON, BURN OR TORCH ON OR NEAR, ANY EPOXY MATERIAL. HAZARDOUS VAPOR IS RELEASED WHEN AN EPOXY IS BURNED.**

### **FOR INDUSTRIAL USE ONLY**

### **WARRANTY AND DISCLAIMER**

Copps Industries, Inc. gives no warranty, express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product. Copps Industries, Inc. shall be in no way responsible for the proper use and service of the product. The information given in this publication is considered to be accurate and reliable and is provided as a service only. Physical properties shown are typical. Actual properties are dependent on curing conditions and degree of cure. Any information or suggestions given are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.