

# COPPS INDUSTRIES GROUT - CHEMICAL RESISTANCE GUIDE

	<u>K-005</u>	<u>K-028</u>	<u>K-027</u>	<u>K-009</u>	<u>K-011</u>	<u>K-021</u>	<u>K-052</u>
<b><u>CHEMICAL</u></b>							
WATER	E	E	E	E	E	E	E
10% ACETIC ACID	NR	G	E	E	F	F	E
50% PHOSPHORIC ACID	NDA	NDA	NDA	E	E	NDA	E
10% SULFURIC ACID	NR	NR	E	E	E	E	E
50% SULFURIC ACID	NR	F	E	E	E	NR	E
70% SULFURIC ACID	NDA	NDA	E	E	E	NDA	E
10% HYDROCHLORIC ACID	E	G	E	E	E	E	E
36% HYDROCHLORIC ACID (CONC)	NDA	NDA	NDA	E	F	NDA	E
10% NITRIC ACID	E	E	E	E	E	E	E
30% NITRIC ACID	NDA	NDA	NDA	E	F	NDA	E
AMMONIUM HYDROXIDE	E	E	E	E	E	E	E
AMMONIUM HYDROXIDE (CONC)	E	E	E	E	E	E	E
50% SODIUM HYDROXIDE	E	E	E	E	E	E	E
METHANOL	NR	NR	F	E	NR	NR	E
XYLENE	F	E	E	E	E	E	E
MINERAL SPIRITS	E	E	E	E	E	E	E
ACETONE	NR	G	NR	NR	NR	NR	E
TRICHOLORETHANE	NR	E	E	G	E	E	E
MOTOR OIL	E	E	E	E	E	E	E
UNLEADED GASOLINE	E	E	E	E	E	E	E
LEADED GASOLINE	E	E	E	E	E	E	E
DIESEL FUEL	E	E	E	E	E	E	E
KEROSENE	E	E	E	E	E	E	E
15% SODIUM HYPOCHLORITE	E	E	E	E	E	E	E

E = EXCELLENT    G = GOOD    F = FAIR    NR = NOT RECOMMENDED    NDA = NO DATA AVAILABLE

NOTE: ALL PRODUCTS IMMERSED FOR 30 DAYS AT 72 °F: CURE CYCLE = 7 DAYS AT 72 °F PRIOR TO IMMERSION. K-052 CURED 24 HOURS AT 72 °F + 4 HOURS AT 200 °F + 4 HOURS AT 350 °F.

ALL RATINGS ARE BASED ON % WEIGHT GAIN OR LOSS.

TB#5008 (02/01)