

## Fast Structural Strengthening Epoxy – A-018/B-425

### Description:

Fast Structural Strengthening Epoxy is two-component, 100% solids, high strength, impregnating epoxy matrix material for bonding applications. The matrix material is combined with fabrics to provide a wet-layup composite system for strengthening structural members.

### Handling Properties:

|                      |              |             |
|----------------------|--------------|-------------|
| COLOR                | Clear        |             |
| DENSITY, lb./gal     | 9.13         | ASTM D 792  |
| MIX RATIO, pbv (pbw) | 2/1 (2.45/1) |             |
| MIXED VISCOSITY, Cps | 900          | ASTM D 2196 |
| WORKING TIME*, min   | 60 – 90      |             |

\*The working time varies according to the temperature of the air, the epoxy and the surface to which it is applied.

### Physical Properties:

|                                 |                |             |
|---------------------------------|----------------|-------------|
| TENSILE STRENGTH, psi (MPa)     | 10,800 (74.5)  | ASTM D 638  |
| TENSILE MODULUS, psi (MPa)      | 305,300 (2106) | ASTM D 638  |
| ELONGATION @ BREAK, %           | 3.74           | ASTM D 638  |
| COMPRESSIVE STRENGTH, psi (MPa) | 13,900 (96)    | ASTM D 695  |
| COMPRESSIVE MODULUS, psi (MPa)  | 298,200 (2057) | ASTM D 695  |
| FLEXURAL STRENGTH, psi (MPa)    | 16,700 (115)   | ASTM D 790  |
| HARDNESS, Shore D               | 86D            | ASTM D 2240 |
| Tg, ULTIMATE, DSC, °F (°C)      | 172 (78)       | ASTM D 3418 |

### Surface Preparation:

The surface to be coated must be free of all rust, scale, dirt, dust, grease, oil, release agents, or other contaminants. The more thorough the degree of surface preparation the better the applied epoxy will perform.

### Mixing:

Epoxy kits are supplied with the resin and hardener pre-measured in the correct mixing ratio. It is best to use a full kit at one time to ensure the proper mixing ratio is maintained. If less than a full kit is required for the job, both the resin and hardener **must** be **accurately** measured out. **DO NOT ATTEMPT TO "EYEBALL" THE AMOUNT NEEDED.** Adding more or less hardener will only degrade the physical properties.

If the kit is colder than 60°F (15.6°C), preheat both the resin and hardener by placing the cans in a hot water bath. The water temperature should not exceed 90°F (32.2°C) as high heat will reduce the working time of the mix.

Add hardener content to the resin. Smaller amounts may be mixed by hand using a large spatula. Larger amounts should be mixed with a slow speed drill and mixing paddle until uniform. Generally, this takes 2-3 minutes depending on the method used. Incomplete mixing will result in poor curing, loss of physical properties, and "soft spots".

**Application:**

To use as an impregnating resin for horizontal and vertical applications, apply Fast Structural Strengthening to reinforcing fabric manually or with an automatic impregnator. Fast Structural Strengthening Epoxy can be applied as a prime coat by brush or roller.

**Packaging:**

K-111-13.6 lbs. (1.5 gallons)

K-111- 27.2 lbs. (3 gallons)

**ESTIMATED COVERAGE RATES:**

120 ft<sup>2</sup>/gal. – 9 oz. per sq. yd. fabrics

60 ft<sup>2</sup>/gal. – 18 oz. per sq. yd. fabrics

30 ft<sup>2</sup>/gal. – 37 oz. per sq. yd. fabrics

Additional Coats: 120 ft<sup>2</sup>/gal

**SAFETY PRECAUTIONS**

Avoid breathing of vapors. Forced local exhaust is recommended to effectively minimize exposure. NIOSH approved, organic vapor respirators and forced exhaust are recommended in confined areas, or when conditions (such as heated polymers, sanding) may cause high vapor concentrations. **DO NOT WELD ON, BURN OR TORCH ON OR NEAR, ANY EPOXY MATERIAL. HAZARDOUS VAPOR IS RELEASED WHEN AN EPOXY IS BURNED.**

**WARRANTY AND DISCLAIMER**

Copps Industries, Inc. gives no warranty, express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product. Copps Industries, Inc. shall be in no way responsible for the proper use and service of the product. The information given in this publication is considered to be accurate and reliable and is provided as a service only. Physical properties shown are typical. Actual properties are dependent on curing conditions and degree of cure. Any information or suggestions given are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.

