

ARMORGARD 541 - K-541

Description:	<p>Armorgard 541 is a 100 % solids, thixotropic, primerless, odorless epoxy coating for foam patterns and molds used in precast concrete applications. Armorgard 541 is formulated to provide a hard, tough coating for EPS foam and Styrofoam without the use of hazardous – foam damaging solvents. Use of Armorgard 541 transforms a “rough” foam structure into a hard, sandable surface, creating an “architectural” quality cast. Armorgard 541 provides a convenient work life. Armorgard 541 was designed from conception to be the <u>ideal</u> foam coating. The product is colored for an easy visual check of thickness.</p>		
Product Advantages:	<ul style="list-style-type: none"> • SOLVENT FREE-ZERO VOC • SINGLE COAT APPLICATION • LOW HEAT ON CURE • EXTREMELY TOUGH, NON BRITTLE SURFACE • SEALS HOTWIRE CUT FOAM PATTERNS • DOES NOT DISTORT MOLD SHAPE 		
Application Guidelines:	<p>Normal application thickness is 15-30 mil (0.38-0.76 mm). Application varies depending on the porosity and roughness of the surface. A single build may be applied to horizontal surfaces up to 1/8" thick (125 mil or 0.3 cm). Armorgard 541 is conveniently packaged in 4 gallon, pre-measured kits, or bulk 5 gallon, 55 gallon and 275 gallon totes.</p>		
Handling Properties:	MIX RATIO, pbv	5/1	
	COLOR	Lt. Blue	
	MIXED VISCOSITY, cP or mPa.s	4,500	ASTM D 2196
	WORKING TIME, min	60	
	GEL TIME, min	90	
	TACK-FREE TIME, h	19-20	
	INITIAL CURE, h	24-30	
	APPLICATION TEMPERATURE, °F (°C)		
	Ideal	70-80	(21-27)
	Acceptable	55-90	(13-32)
	COVERAGE* @ 15 mil or 0.38 mm, ft ² /gal (m ² /l)	107	(2.6)
	*Varies with porosity of surface		
Physical Properties:	HARDNESS, Shore D	79	ASTM D 2240
	MAXIMUM SERVICE TEMPERATURE, °F (°C)	175	(79)
	Armorgard 541 will soften when exposed to extreme precast temperatures.		
Surface Preparation:	<p>To achieve excellent adhesion, the substrate should be free of all loose and foreign material and should be clean. If present, any oils, greases, or other contaminants <u>must</u> be removed prior to coating. Armorgard 541 will not bond to a contaminated surface.</p> <p>Relative humidity and dew point must be determined before application to avoid adhesion failures. The dew point is used to predict the substrate temperature at which air begins to condense, in the form of water, on the substrate. Never apply a coating unless the form surface temperature is 5 °F (2.5 °C) above the dew point. This temperature difference must be observed until the epoxy coating is cured to a tack-free state. A dew point calculation chart is available from a Copps Technical Representative.</p>		

Mixing:

Mix 5 parts A (resin) to 1 part B (hardener) for 3 minutes using a Jiffy Mixer and a slow speed drill. Mix at slow speed (less than 500 rpm) to avoid air entrainment. DO NOT mix more material than can be used within the stated working time. REMEMBER - you will have less working time at higher temperatures.

**Curing
Procedures:**

Armorgard 541 can be applied with a squeegee, brush, non-shedding roller or a grooved fiberglass roller. Re-coating a used foam piece may require a light sanding to remove any residue from previous casts.

SAFETY PRECAUTIONS

Armorgard 541, before it is fully cured (hard), may be removed from tools with Copps Enviro Kleen solvent or warm soapy water.

Avoid breathing of vapors. Forced local exhaust is recommended to effectively minimize exposure. NIOSH approved, organic vapor respirators and forced exhaust are recommended in confined areas, or when conditions (such as heated polymers, sanding) may cause high vapor concentrations. **DO NOT WELD ON, BURN OR TORCH ON OR NEAR, ANY EPOXY MATERIAL. HAZARDOUS VAPOR IS RELEASED WHEN AN EPOXY IS BURNED.**

Avoid skin or eye contact. Wash skin with soap and water if contact occurs. If eye contact occurs flush with water for 15 minutes and obtain medical attention. Read and understand all cautions on can labels and safety data sheets before using this material.

FOR INDUSTRIAL USE ONLY**WARRANTY AND DISCLAIMER**

Copps Industries, Inc. gives no warranty, express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product. Copps Industries, Inc. shall be in no way responsible for the proper use and service of the product. The information given in this publication is considered to be accurate and reliable and is provided as a service only. Physical properties shown are typical. Actual properties are dependent on curing conditions and degree of cure. Any information or suggestions given are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights.